




2. Model information.


It is an **Hybrid AV mount** with a anti rollover system incorporated, designed for semi-industrial machines and specially, for the domestic sector. Its hybrid system provides us the best of "helical steel" spring properties for a proper performance in eradicating low frequencies Hz while the great quality polymer "MEGOL" provides us the damping power, for a proper performance in the low and medium frequencies regime Hz.



The juxtaposition of these two components makes possible launching an unique AV mount to the market, avoiding the spread of waves across the structure, and reducing vibrations in the whole exciter frequencies range. Ideal for machines working from 350 rpm.

Application field: Cooling machines, condensers, ventilators, air processing units, air conditioning units, pumps, etc. Through a bank or directly installed on the system it is intended to isolate.









Generally, the gravity center is not coincident with the geometric center.

As we can see in the left picture, the unit is formed by different components: Compressor, condenser, controls, etc. These elements are located in one end, and the air extraction in the opposite end. So we can detect that 70% of the load will be located in the compressor area, and 30% remaining will be located in the ventilation area. The TBMF-ANTI ROLLOVER range has the advantage of combining 4 colors to differentiate the load quantity per unit (Kg).

Grey, Green, Blue and Red. The grey color shows the lowest one, while red color shows the maximum load. In this way, we can treat the unit properly, placing the proper damper according to the load distribution.





5. Calculation Procedure.

It is about determining the static deflection of the steel springs, for different load values.

Using this data, and under the supposition of linear systems, we can determine the elastic constant of springs.

A spring performs a force which is proportional to its deformation:

$$F = k \delta$$

Where:

F = Spring force.

k = Rigidity.

 δ = spring deformation.

Note: For systems with linear behavior (**steel spring**), the dynamic rigidity equals the elastic rigidity. However, in case of polymeric viscoelastic materials (Polyurethane, EPDM, Polystyrene, Polyethylene, etc.), they are never coincident, and its dynamic behavior can only be determined through a lab essay.

Generally, steel springs have an optimal behavior in a frequency range from 300 and 2500 rpm.

The resonance frequency of the spring + the machine is given by::

$$w_0 = \sqrt{\frac{K}{m}}$$

Where:


 $w_0 = system resonance frequency$.

(rad/s)

k = spring rigidity (N/m).

m = system mass (machine).


If k nor m are not known when calculating the system resonance frequency, it is calculated through its static flexion.




$$m g = K \delta \Re \frac{K}{m} = \frac{g}{\delta}$$

Introducing such result in the expression:

$$w_0^2 = \frac{K}{m} \Rightarrow w_0 = \sqrt{\frac{K}{m}} = \sqrt{\frac{g}{\delta}}$$
$$\left(w_0 = 2\pi f\right)$$






$$FT = \frac{F_t}{F_0} = \frac{1}{\left|1 - \rho^2\right|}$$

Vibratory isolation degree given in %

$$G = (1 - FT)100$$
 (%)

The behavior of the spring will depend on how they are placed.



6. Chart of maximum results.

REFERENCIAS	FUERZA máxima (N)		Floobe (mm)	Disides (NI/mm)
	Fuerza (N)	Frecuencia Propia (Hz)	Flecha (mm)	Rigidez (N/mm)
REFERENCES	Force (N)	Natural Frequency (Hz)	Deformation (mm)	Rigidity (mm)
SE-TBMF 20	200	3,78	11,30	17,70
SE-TBMF 45	450	3,95	11,90	37,70
SE-TBMF 75	750	4,00	11,90	62,80
SE-TBMF 120	1200	3,86	11,40	105,70

"SENOR"; reserves the right to change the technical specifications of the product without previous notification. The user is the final responsible for knowing and using the updated last version of data sheets of products. A copy will be sent to anyone who request it. This information and, in particular, the application recommendations and final usage of the product, are given in good faith, based on our current knowledge and the experience of "SENOR" of its products, when these are properly installed in normal circumstances and within its useful life.



7. Technical Data Hybrid + Grey MEGOL.

Product: MEGOL I A 25 C UG/UVI GREY F761 P1250SPE25

Density - ASTM D 792 - g/cm3 - 1.15 / 1.19

Hardness "15sec" - ASTM D 2240 - Shore A - 20 / 25

Extreme force - ASTM D 624 - KN/m - 11 / 19

Ultimate tensile strength - ASTM D 638 - MPa - >3.5

Elongation % break - ASTM D 638 - % - >800

A Core formed by a steel spring of 3,66 mm thick (Standard DIN 2095-UNI EN 10270), with EPOXY treatment Red RAL 330. It provides a high isolation degree from vibrations, in the range of low/medium frequencies Hz.

Procedure

- Determination of dynamic behavior.
- Load Curve and deformation.

Determination of dynamic behavior.

It is about determining the natural frequency (Hz) and the deformation for different load values, over the shock absorber. A frequency sweep is done for each load state between 0-100 Hz at a given acceleration level (0.2 g). Placing an acceleration at the rigid part of the structure which serves for control and other on a rear point to the action of the shock absorber, where we will get the results which determine the shock absorber performance.

Used Equipment:

Accelerometers signal amplifier.

PCB / Code ME 084030

Accelerometer


PCB / Code ME 072021

Essays Machine

NOGREN / Code ME 035002

Vibratory table

LDS / Code ME 075001






MEGOL I A 25 C UG/UVI GREY F761. P1250SPE25

Graph Data

DEFORMATION (MM)	NATURAL FREQUENCY(HZ)	LOAD (KG)
2,3	9,50	4
4,5	6,42	8
6,8	5,06	12
9,0	4,25	16
11,3	3,78	20
13,5	4,29	24

The performance line shows the beginning and the end of the work performed by the HYBRID + GREY MEGOL system, 6 Kg and 20 Kg respectively. Vertical bars in dark Grey color provide the following info:

- Deformation in millimeters.
- Load process in each deformed point.
 Optimal degree of elasticity.



Conclusion: The shock absorber TBMF-20 is placed on the hydraulic piston for its compression test, applying the load in a progressive way at a speed of 2 mm/min, until a maximum of 0,25 kN. Load and movement data are obtained.

When data is transferred to the dynamic graph, it shows that vertical bars which surpass the performance line in a higher level are bars no 2, 3, 4, and 5. These bars show us the optimal degree of elasticity. Therefore, the recommended loads to be used.



8. Technical Data Hybrid + Green MEGOL.

Product: MEGOL I A 30 C UG/UVI GREEN F084/E

P1250SPE25

Density - ASTM D 792 - g/cm3 - 1.19

Hardness "15sec" - ASTM D 2240 - Shore A - 27 / 35

Extreme force - ASTM D 624 - KN/m - 13

Ultimate tensile strength - ASTM D 638 - MPa - >5.1

Elongation % break - ASTM D 638 - % - >817

A Core formed by a steel spring of 4,20 mm thick (Standard DIN 2095-UNI EN 10270), with EPOXY treatment Red RAL 330. It provides a high isolation degree from vibrations, in the range of low/medium frequencies Hz.

Procedure

- Determination of the dynamic behavior.
- Load curve and deformation.

Determination of the dynamic behavior.

It is about determining the natural frequency (Hz) and the deformation for different load values, over the shock absorber. A frequency sweep is done for each load state between 0-100 Hz at a given acceleration level (0.2 g). Placing an acceleration at the rigid part of the structure which serves for control and other on a rear point to the action of the shock absorber, where we will get the results which determine the shock absorber performance.

Used Equipment:

Accelerometers signal amplifier.

PCB / Code ME 084030

Accelerometer


PCB / Code ME 072021

Essays Machine

NOGREN / Code ME 035002

Vibratory table

LDS / Code ME 075001






MEGOL I A 30 C UG/UVI GREEN F084/E. P1250SPE25

Graph Data

Grapii Data					
DEFORMATION (MM)	NATURAL FREQUENCY (HZ)	LOAD (KG)			
4,0	6,90	15			
5,3	5,84	20			
6,6	5,12	25			
8,0	4,59	30			
9,3	4,17	35			
10,6	4,05	40			
11,9	3,95	45			
13,3	4,33	50			

The performance line shows the beginning and the end of the work performed by the HYBRID + GREEN MEGOL system, 15 Kg and 45 Kg respectively. Vertical bars in dark Green color provide the following info:

- Deformation in millimeters.
 Load process in each deformed point.
- Optimal degree of elasticity.



Conclusion: The shock absorber TBMF-45 is placed on the hydraulic piston for its compression test, applying the load in a progressive way at a speed of 2 mm/min, until a maximum of 0,50 kN. Load and movement data are obtained.

When data is transferred to the dynamic graph, it shows that vertical bars which surpass the performance line in a higher level are bars no 3, 4, 5, 6, 7, 8 and 9. These bars show us the optimal degree of elasticity. Therefore, the recommended loads to be used.



9. Technical data Hybrid + Blue MEGOL.

Product: MEGOL I A 40 C UG/UVI BLUE F085/E P1250SPE25

Density - ASTM D 792 - g/cm3 - 1.25

Hardness "15sec" - ASTM D 2240 - Shore A - 36 / 42

Extreme force - ASTM D 624 - KN/m - 16

Ultimate tensile strength - ASTM D 638 - MPa - >5.6

Elongation % break - ASTM D 638 - % - >960

A Core formed by a steel spring of 4,20 mm thick (Standard DIN 2095-UNI EN 10270), with EPOXY treatment Red RAL 330. It provides a high isolation degree from vibrations, in the range of low/medium frequencies Hz.

Procedure

- Determination of the dynamic behavior.
- Load curve and deformation.

Determination of the dynamic behavior.

It is about determining the natural frequency (Hz) and the deformation for different load values, over the shock absorber. A frequency sweep is done for each load state between 0-100 Hz at a given acceleration level (0.2 g). Placing an acceleration at the rigid part of the structure which serves for control and other on a rear point to the action of the shock absorber, where we will get the results which determine the shock absorber performance.

Used Equipment:

Accelerometers signal amplifier.

PCB / Code ME 084030

Accelerometer

PCB / Code ME 072021

Essays Machine

NOGREN / Code ME 035002

Vibratory table

LDS / Code ME 075001

